



Investigation Of Tribological Behavior Of Peek With Carbon Filled Composites Under Harsh Operating Conditions.

#1Mr.Karpe Ganesh G, #2Dr. C.L. Dhamejani

¹karpeganesh03@gmail.com

²Chetan_dhamejani@rediffmail.com

#1Department of Mechanical Engineering,JCOE, Kuran, Savitribai Phule Pune University, MH, India.

#2Principal Jaihind College of Engineering, Kuran Savitribai Phule Pune University, MH, India.

ABSTRACT

The present work describes the development and characterization of a new set of hybrid polymer composites consisting of Polyether-ether-keton and PTFE. This work reports the development and wear performance evaluation of a new class of poly-ether-ether-ketone (PEEK) based composites filled PTFE as filler material. The effects of various contact temperatures on the tribological properties of PTFE/PEEK composites were studied under dry as well as wet friction conditions. PEEK composites are often used as compressor piston rings or valve for their outstanding mechanical and thermal performance at high temperature conditions, where PTFE composites may fail to service. However high friction coefficient and wear rate of pure PEEK limit its wider use. Many researchers found that PEEK is good in mechanical characteristic but inferior performances of tribological properties. The effect on the friction and wear nature of PEEK polymer composites has been improved, with addition of PTFE at room temperature. There are various operations performed in industry at elevated temperature on different machines and high wear rate at elevated temperature is a serious problem in a large number of industrial applications. The objective of this work will be to study the friction and wear properties of PEEK filled with PTFE at elevated temperature as well as to increase tribological behavior of PEEK without loss of mechanical properties at elevated temperature with addition of suitable filler material.

Keywords— composites,elevated,filler material, PTFE,PEEK,tribological.

ARTICLE INFO

Article History

Received :18th November 2015

Received in revised form :

19th November 2015

Accepted : 21st November , 2015

Published online :

22nd November 2015

I. INTRODUCTION

Polymer-ether ether- ketone (PEEK) is a semi-crystalline, high performance engineering thermoplastic with a very good combination of thermal (Carbon =143°C,Tm= 343°C, continuous service temperature 250°C, heat distortion temperature often in excess of 300°C and better mechanical strength, modulus, toughness, resistance to creep, abrasion

and good fatigue strength. It is injection as well as compression moldable polymer with good resistance to harsh chemical environment (Bijwe, J. et al, 2005) For last 15 years, it has been focus of research for enhancing its tribo-potential in various ways and review articles updating the state of art of PEEK tribology have also appeared from time(Zhuang G.S. et al,2007) . In spite of its fairly good resistance to adhesive wear, it has serious drawback from a

tribological point of view. It is known to exhibit a coefficient of friction as high as 0.7 under some operating conditions, which limits its utility as an anti-friction material. Another potential problem with this material, is its scuffing behavior (Feng, Xin, et al, 2008). Development and tribo-evolution of various blends of PEEK to enhance its Carbon with some high temperature polymer such as poly ethamide (Lal, B.S. et al, 2007), thermo tropic liquid crystal polymer (Friedrich, J.K. et al, 2005) and PTFE (Breidt, C. et al, 2004) have also been tried. Very low coefficient of friction (as low as 0.1) without scuffing at high pressure velocity and very low in the range of 10^{-6} /Nm. The high wear rate at high temperature is a serious problem in a large number of industrial applications such as elevated temperature compressor piston rings and bearings (Taktak S et al, 2006). Meanwhile, to meet the combination of light weight and high strength demands, polymer-based materials are increasingly applied in many industries. However, at temperatures above 180°C is a challenge for most of the polymer composites (West, G.H. et al, 1973), PEEK composites are expected to have excellent high-temperature tribological properties due to their outstanding mechanical and thermal performances above 180°C, where polytetrafluoroethylene (PTFE) composites will meet severe creep behaviors. However, high friction coefficient and big (Lu and Friedrich et al, 2005) wear rate of pure PEEK limit its wider use. Resistance and compressive strength of the polymer composites and result in enhanced wear resistance. Among numerous inorganic fillers, Bronze has been found to be a promising structural reinforce for polymers, metals, and ceramic composites because of its excellent reach. The objective of this research is to find friction and wear mechanisms of different fibers-filled PEEK composites at elevated temperatures. It is also expected that this work can be helpful to the use for bearing, compressor piston rings, impeller, etc. at elevated temperatures.

II. EXPERIMENTAL

A. PREPARATION OF MATERIALS

Commercially available Polyetheretherketon (PEEK) of grade 450G fine powder with the average diameter of 100µm was supplied by Victrex. The polytetrafluoroethylene (PTFE) powder with the diameter smaller than 60µm was provided by PCEE Textile Kanpur Bronze powder with 10% tin was supplied by Pometon India Ltd. Molybdenum disulfide powder of diameter 100µm also supplied by Vishal Pharmachem Mumbai. The composite were prepared by compression as well as injection molding. First PEEK, PTFE, and Carbon Fiber were mixed with different proportion for various batches with batch size 100gm for compression molding and 15 gm. For injection molding. For accurate weighing digital weighing balance are used with accuracy 0.0001gm for uniform mixing were done by compounding of raw materials. a. Compounding: The compounding of materials were done at Central Institute of Plastic Technology, (CIPET) Bhubaneswar, Orissa. Compounding was done before specimen preparation so that would form uniform mixture or homogeneous mixture. For compounding of raw material. Twin screw extruder are used during compounding of material firstly the PEEK,

PTFE, Carbon Fiber were weighed on digital weighing machine with weight measuring accuracy 0.0001gm. This compounding was done by compression molding, the PEEK, PTFE and Carbon Fiber which all were in powder form were mixed proportionally in china crucible and steered by china spoon. The prepared mixture were poured by stainless steel spoon slowly inside the Twin-screw extruder which was sated at temperature of 400°C and screw speed were kept 120 rpm, so that extruded material pallets form during extrusion would be extruded and that would be handled properly. The extruded pallets were undergoing water bath so that they can cool down soon and could not be broken into small pallets which would be difficult to handle. The long thread like pallets was collected and then it would be again cut into small granules by using pallet cutter machine. These small granules were collected in poly bag and coded it for further specimen process. Same procedure was used for all three types of combination and all were packed in poly bag and bags were coded with code S1, S2, & S3. Before the compression molding the prepared granules were dried in hot electric furnace about 1hr at 80°C in order to remove moisture present in it. The dried granules then underwent compression molding with pressure 120MPa and temperature 400°C as the processed based material PEEK whose melting temperature is 343°C and when it goes compounding its processing temperature required would be up to 400°C so that it can be processed properly. The compression test was carried out near about for 3hrs. With the help of compression molding sheet of dimension 100mm×100mm×6mm with weight of 75g was prepared. The sample specimens were cut into small pins of dimension 6mm×6mm×30mm. These samples were grind for surface finishing on fine grinder as well as various fine grade emery papers were used for perfect flat surface so that zero clearance were maintain between pin and disc. In such a way 03 pins with code S1, S2 & S3 were ready for testing on Tribo meter TR-20. for elevated temperature test. Compounding by micro compounder: The specimen for mechanical testing as well as tribo-testing made by injection molding. This micro compounding facility available at CIPET Bhubaneswar. For micro compounding same all raw material like PEEK, PTFE and Carbon Fiber weighted with digital weighing balance 15gm per batch, contains all four powder material with different percentage. In micro compounder the processing temperature for PEEK were kept at 400°C. The batch of 15gm was poured step by step and allows melting 30 minute so that complete homogeneous mixture would be formed. During processing of mixture the processing temperature are kept 400°C. This temperature are divided into six temperature zone. The temperature profile were kept 390°C, 350°C, 341° front side and 340°C, 350°C, 392°C for rear side for proper mixing and melting step by step. The maximum axial torque or axial forces are selected up to 8000N. For processing of PEEK material maximum force value were required 4037N. This force value increasing in ascending order from top side to The molten mixture were collected in gun which is also maintain at processing temperature 400°C in order to prevent hardening of PEEK material as its soaking period is very small. The collected molten mixture was injected into die with help of injection molding machine and sample were prepared for mechanical as well as tribological test. Selection of counterpart: the counterpart ie disc is selected

with consideration of application like air compressor. The generally the cylinder liner for air compressor or cylinder is made up by stainless steel or grey cast iron with this reference the counterparts also selected as made up of same material. So the disc material was selected steel with grade EN38 and grey cast iron with dimension $\text{Ø}165\text{mm} \times 8\text{mm}$ thickness made ready for test. After that disc hardness was checked by Brinell hardness Tester and surface roughness $0.4\mu\text{m}$ was checked at Vishal Engineering.

B. Wear Test

The prepared samples were used for tribological test for elevated temperature at P. Dr. V.V Patil College of Engineering Ahamednagar, Maharashtra. The Wear was performed on a pin-on disc apparatus according to ASTM D2538 and ASTM D2396. The test rig was supplied by DUCOM Instrument Bangalore, show in fig.1 Initially the calculations were done before test. Specially the wear tests were conducted for non-lubricating reciprocating compressor piston ring. The basic aim was that to minimize wear rate and fine better material for piston rings of non-lubricating reciprocating compressor. The Specimen pin ($4 \times 4 \times 30\text{ mm}^3$) was run against the polished steel disc of grade EN-38 with an initial surface roughness of 0.4μ . With contact pressure ranges from 1 to 4MPa. The value of contact pressure were selected with no lubricating air compressor application which works at working pressure at 4MPa and sliding velocity were selected in the range from 1.8m/s to 3.4m/s. To evaluated the durability at elevated of material at elevated temperature, the pin was kept in the temperature controlled environment ie Pin holder or collet was kept inside the collet holder which is has provides heating device. The electrical heating device was controlled by microcontroller in various ranges. The variation in the temperature of collet is in the steady sate was less than $\pm 5^\circ\text{c}$. during the test load values were selected from ranges 10N to 50N. and temperature were kept from 100°c to 250°c as glass transition temperature of PEEK is 143°c and melting temperature is 343°c as per standard data supplied by Victrex. Also another aim for keeping the temperature from 100°c to 250°c has taken specific application of ATLAS CAPCO non lubricating reciprocating air compressor. The generally discharge temperature of compressed air vary from ambient to 70°c as compressor run continuously long time. Also similarly all parameter like sliding velocity, load and temperature parameter were selected on basis of considering same application. During the test first specimen with code S1 were holed in a temperature environment and initial temperature was sated at 100°c , load 10 N and sliding velocity 1.8m/s. as input parameter for wear and frictional force measurement. During the test, the frictional coefficient was recorded and calculated by a ratio between the tangential force and normal load. This is also monitored by placing load cell transducers. The test temperature was monitored by an iron-constantan thermocouple positioned in the hole of collet where pin specimen was fitted. The reduction in height of the specimen was measured by a displacement transducer, could be used to characterize the wear process. However the reliability of this measurement was affected by the possible thermal expansion of the sliding counterparts. There for after the test the mass loss of the specimen was measured to calculate the specific were rate by the equations.



Fig.1 Wear and friction measuring test rig.



Fig 2 Specimen obtained by injection moulding.

III. CONCLUSIONS

- 1) PEEK is one of the few polymers that can be considered for use as a true metal replacement for high temperature applications. As one of the first designer polymers, the superb range of properties has opened up new and highly demanding markets for plastics. Initially, PEEK was considered an exotic material, but now it is an essential tool in the materials engineer's armory for applications when no other material can meet the requirements
- 2) The outstanding mechanical properties of PEEK at high temperatures make it suitable for the most emending applications, but the high cost sometimes limits applications to those where the properties are very necessary.
- 3) PTFE in PEEK definitely and significantly improved the performance of PEEK. The blends did not show any scuffing problems.
- 4) Except for impact behavior, all the mechanical properties of the blends deteriorated with increase in PTFE% in PEEK., PEEK exhibited the best mechanical properties and abrasive wear resistance

ACKNOWLEDGEMENT

I take this opportunity to thank all those who have contributed in successful completion of this Project Stage-I work. I would like to express my sincere thanks to my guide Dr. C.L . Dhamejani, who has encouraged me to work on this topic and valuable guidance wherever required. I wish to express my thanks to Prof. H. Mishra, Head, Mech Design Engg. Dept., Prof. R. S. Mulajkar P.G. Co-ordinator for their support and the help extended. Finally, I am

thankful to all those who extended their help directly or indirectly in preparation of this report.

REFERENCES

- [1] G.S. Zhuang, G.X. Sui, H. Meng, Z.S. (2007) , “ Mechanical properties of potassium titanate whiskers reinforced poly(ether ether ketone) composites using different compounding processes”, *Composites Science and Technology*. Institute of Metal Research, Chinese Academy of Sciences, Shenyang, China.
- [2] Liwen mu, XIN FENG, YIJUN SHI.,(2010), “Comparative Study of Tribological Properties of Different Fibers Reinforced PTFE/PEEK Composites at Elevated Temperatures”, State Key Laboratory of Materials-Oriented Chemical Engineering, Nanjing University of Technology, Nanjing, China.
- [3] Mu Liwena, FengXin , Zhu Jiahuaa, (2008), “Comparative Study of Tribological Properties with Different Fibers Reinforced PTFE/PEEK Composites at Elevated Temperatures”, College of Chemistry & Chemical Engineering, Daqing Petroleum Institute, Daqing, China.
- [4] B. Lal, S. Alam, G.N. Mathur, (2007) , “ Tribo-investigation on PTFE lubricated PEEK in harsh operating conditions”,. Polymer Science Division, Defence Materials Research and Development Establishment, Kanpur, India.
- [5] J. Bijwe, S. Sen, A. Ghosh, (2005) “ Influence of PTFE content in PEEK-PTFE blends on mechanical properties and tribo-performance in various wear modes”, *Wear* 258 -1536–1542.
- [6] K. Friedrich, Z. Zhang, A.K. Schlarb, (2005) “ Effects of various fillers on the sliding wear of polymer composites”, *Composites Science and Technology* 65.
- [7] J.J. Rajesh, J. Bijwe, U.S. Tewari, (2001) “ Influence of fillers on abrasive wear of short glass fibre reinforced polyamide composites”, *Journal of Materials Science* 36- 351–356.
- [8] Z. Zhang, C. Breidt, L. Chang, K. Friedrich, (2004) “ Wear of PEEK composites related to their mechanical performances”, *Tribology International* 37 (2004) 271–277.
- [9] T. Sinmazcelik, T. Yilmaz, Thermal aging effects on mechanical and tribological
- [10] Zhang, G., Yu, H., Zhang, C., Liao, H. and Coddet, C. (2008), “Temperature Dependence of the Tribological Mechanisms of Amorphous PEEK (Polyetheretherketone) under Dry Sliding Conditions,” *Acta Mater.*, 56, 10, pp 2182-2190.
- [11] Burris, D.L. and Sawyer, W.G. (2006), “A Low Friction and Ultra Low Wear Rate PEEK/PTFE Composite,” *Wear*, 261, pp 410-418.
- [12] JWest, G.H. and Senior, J.M. (1973), “High Temperature Plastics Bearing Compositions,” *Tribology*, 6, 6, pp 269-275.
- [13] Lu, Z.P. and Friedrich, K. (1995), “On Sliding Friction and Wear of PEEK and Its Composites,” *Wear*, 181-183, pp 624-631
- [14] H` ager, A.M., Friedrich, K. Junghans, R. (1993), “Selected Thermoplastic Bearing Materials for Use at Elevated Temperatures,” *Wear*, 162-164, pp 649-655
- [15] Chang, L., Zhang, Z., Ye, L. and Friedrich K. (2007), “Tribological Properties of High Temperature Resistant Polymer Composites with Fine Particles,” *Tribol. Int.*, 40, pp 1170-1178.